

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : B01D 71/64, 61/02, 69/12, C10G 31/11	A1	(11) International Publication Number: WO 00/06293 (43) International Publication Date: 10 February 2000 (10.02.00)
(21) International Application Number: PCT/US99/15603 (22) International Filing Date: 12 July 1999 (12.07.99) (30) Priority Data: 09/126,261 30 July 1998 (30.07.98) US (71) Applicant: W. R. GRACE & CO.-CONN. [US/US]; 1114 Avenue of the Americas, New York, NY 10036 (US). (72) Inventor: WHITE, Lloyd, Steven; 5070 Summer Day Lane, Columbia, MD 21044 (US). (74) Agent: MAGGIO, Robert, A.; W. R. Grace & Co.-Conn., 7500 Grace Drive, Columbia, MD 21044 (US).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: POLYIMIDE MEMBRANES FOR RECOVERY OF AROMATIC SOLVENTS UNDER HYPERFILTRATION CONDITIONS (57) Abstract Symmetric hyperfiltration membranes and their method of preparation and use are disclosed. The membranes are fashioned from polyimides and conditioned with a lubricating oil. Permselective separation of aromatic hydrocarbons from non-aromatic hydrocarbons in a feed stream may be accomplished using the membranes under hyperfiltration conditions.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakistan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LJ	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

POLYIMIDE MEMBRANES FOR RECOVERY OF AROMATIC SOLVENTS UNDER HYPERFILTRATION CONDITIONS

5 FIELD OF THE INVENTION

The present invention relates to improved asymmetric membranes fashioned from a polyimide and the method of preparing the membranes. The invention also relates to the method of using the membranes for the separation of aromatic hydrocarbons from non-aromatic hydrocarbons under
10 hyperfiltration conditions.

Of particular interest, the membranes are useful for the recovery of aromatic hydrocarbons, i.e. toluene, having a high purity from process streams containing aromatic and non-aromatic hydrocarbons during a commercial process for the production of aromatic hydrocarbons.

15

BACKGROUND OF THE INVENTION

The separation of aromatics from non-aromatics is useful in upgrading aromatics containing streams in petroleum refineries, such streams including, naphtha streams, heavy catalytic naphtha streams, intermediate catalytic
20 naphtha streams, light aromatic streams and reformate streams, and in chemical operations for the recovery of aromatics such as benzene, toluene, xylenes, naphthalene, etc.

The use of membranes to separate aromatics from saturates has long been pursued by the scientific and industrial community. Methods of
25 membrane separation include hyperfiltration (also known as reverse osmosis in aqueous separations), pervaporation and perstraction. Pervaporation relies on vacuum on the permeate side to evaporate the permeate from the surface of the membrane and maintain the concentration gradient driving force which drives the separation process. In perstraction, the permeate molecules in the
30 feed diffuse into the membrane film, migrate through the film and reemerge on

the permeate side under the influence of a concentration gradient. A sweep
flow of liquid or gas is used on the permeate side of the membrane to maintain
the concentration gradient driving force. In contrast, hyperfiltration does not
require the use of external forces on the permeate side of the membrane, but
5 drives the separation through application of a pressure gradient.

Membrane separation of aromatics from saturates has been the subject
of numerous patents.

U.S. Patent No. 3,370,102 describes a general process for separating a
feed into a permeate stream and a retentate stream and utilizes a sweep liquid
10 to remove the permeate from the face of the membrane to thereby maintain the
concentration gradient driving force. The process can be used to separate a
wide variety of mixtures including various petroleum fractions, naphthas, oils,
hydrocarbon mixtures. Expressly recited is the separation of aromatics from
kerosene.

U.S. Patent No. 2,958,656 teaches the separation of hydrocarbons by
type, i.e., aromatic, unsaturated, saturated, by permeating a portion of the
mixture through a non-porous cellulose ether membrane and removing
permeate from the permeate side of the membrane using a sweep gas or liquid.
Feeds include hydrocarbon mixtures, naphtha (including virgin naphtha,
20 naphtha from thermal or catalytic cracking, etc.).

U.S. Patent No. 2,930,754 teaches a method for separating
hydrocarbons e.g., aromatic and/or olefins from gasoline boiling range
mixtures, by the selective permeation of the aromatic through certain cellulose
ester non-porous membranes. The permeated hydrocarbons are continuously
25 removed from the permeate zone using a sweep gas or liquid.

U.S. Patent No. 4,115,465 teaches the use of polyurethane membranes
to selectively separate aromatics from saturates via pervaporation.

U.S. Patent No. 4,929,358 teaches the use of polyurethane membranes
for the separation of aromatics from non-aromatics. Permeation is conducted

under pervaporation, perstraction, reverse osmosis, or dialysis conditions.

None of the experimental results reported in this patent were obtained under reverse osmosis conditions.

Polyimide membranes have been used for the separation of aromatics.

5 U.S. Patent 4,571,444 teaches the separation of alkylaromatics from aromatic solvents using a polyimide polymer membrane. The polyimide membrane of choice was an asymmetric polyimide polymer membrane prepared from a fully imidized, highly aromatic polyimide copolymer. Permeation was performed under reverse osmosis conditions.

10 U.S. Patent 4,532,029 discloses the use of an asymmetric polyimide membrane for the separation of aromatics from lower aromatic middle distillate feeds. Permeation of the feeds in the presence of a light polar solvent, e.g., acetonitrile, was required to obtain permeates having a high aromatic content, i.e., greater than 86%.

15 The majority of investigations for aromatic/non-aromatic separations have heretofore involved pervaporation or perstraction separation techniques. This is probably due to reports of prior literature that very high operational pressures are required in hyperfiltration to reach a equivalent performance achievable by pervaporation and perstraction processes. Unfortunately,
20 pervaporation and perstraction separation systems are higher cost than a hyperfiltration system due to expenses associated with vacuum, refrigeration and heat transfer systems.

Consequently, it is an advantage of this invention to provide improved asymmetric polyimide membranes for the separation of aromatic hydrocarbons
25 from non-aromatic hydrocarbons in a feed stream by hyperfiltration. It is also an advantage of this invention to provide a method of preparing the membrane by a phase inversion technique, which method permits variations in processing conditions to optimize the selective permeation of aromatic hydrocarbons through the membranes in the presence of non-aromatic hydrocarbons.

Another advantage of the invention is to provide a membrane useful in a process of separating aromatic hydrocarbons as described in copending Application Serial No. 126,256, filed July 30, 1998, entitled "Recovery of Aromatic Hydrocarbons Using Lubricating Oil-Conditioned Membranes", Mobil Attorney Docket No.10043-1, filed on even date herewith.

Other facets and advantages of the present invention will be apparent from the ensuing description and the appended claims.

SUMMARY OF THE INVENTION

Improved asymmetric membranes which have high selectivity to permeate aromatic hydrocarbons in the presence of non-aromatic hydrocarbons under hyperfiltration conditions have been found. The membranes are prepared from a polyimide by a phase inversion technique and are thereafter treated with a lubricating oil to condition the membranes.

Membranes in accordance with the invention exhibit over 30% rejection of the non-aromatic hydrocarbon materials at a commercially adequate flow rate in a temperature range of about -20 to 150° C.

Using the membranes of the invention, permselective separation of aromatic hydrocarbons from non-aromatic hydrocarbons in a feed stream may be accomplished by hyperfiltration with sufficient flux and selectivity to offer improved economics over pervaporation conditions. However, it is not intended to limit the use of the membranes to hyperfiltration mode of operation.

A process for using the membrane of the present invention is disclosed in co-pending Application Serial No. 126,256, filed July 30, 1998, entitled "Recovery of Aromatic Hydrocarbons Using Lubricating Oil Conditioned Membranes", Mobil Attorney Docket No. 10043-1, filed on even date herewith.

DETAILED DESCRIPTION OF THE INVENTION

The term "aromatic hydrocarbon" is used herein to designate a hydrocarbon-based organic compound containing one or more aromatic rings.

An aromatic ring is typified by benzene having a single aromatic nucleus.

5 Aromatic compounds having more than one aromatic ring include, for example, naphthalene, anthracene, etc. Preferred aromatic hydrocarbons useful in the present invention include those having 1 to 2 aromatic rings.


The term "non-aromatic hydrocarbon" is used herein to designate a hydrocarbon-based organic compound having no aromatic nucleus.

10 For purposes of this invention, the term "hydrocarbon-based organic compound" is used to mean an organic compound having a predominately hydrocarbon character. It is contemplated within the scope of this definition that a hydrocarbon compound may contain at least one non-hydrocarbon radical (e.g., sulfur or oxygen) provided that said non-hydrocarbon radicals do
15 not alter the predominant hydrocarbon nature of the organic compound and/or do not react to alter the chemical nature of the polyimide of the membrane within the context of the present invention.

Asymmetric membranes are defined for purposes of this invention as an entity composed of a dense ultra-thin top "skin" layer over a thicker porous
20 substructure of the same or different material. Typically, the asymmetric membrane is supported on a suitable porous backing or support material.


Polyimide membranes of the invention can be produced from a number of polyimide polymer sources. The identity of such polymers are presented in numerous patents. See, for example, U.S. Patent No. 4,307,135, U.S. Patent
25 No. 3,708,458, U.S. Patent No. 3,789,079, U.S. Patent No. 3,546,175, U.S. Patent No. 3,179,632, U.S. Patent No. 3,179,633, U.S. Patent No. 3,925,211, U.S. Patent No. 4,113,628, U.S. Patent No. 3,816,303, U.S. Patent No. 4,240,914, U.S. Patent No. 3,822,202, U.S. Patent No. 3,853,754 and British Patent No. 1,434,629.

A preferred polyimide polymer useful to prepare the membranes of the invention is available as Matrimid 5218 from Ciba Geigy. The structure of the polyimide, Matrimid, is shown below. The polyimide is also known as the polymer with 1 (or 3)-(4-aminophenyl)-2,3-dihydro-1,3,3 (or 1,1,3)-trimethyl-1H-inden-5-amine and 5,5'-carbonylbis-1,3-isobenzofurandione (CAS Number 62929-02-6). A common name for Matrimid is the polymer with diaminophenylindane and benzophenone tetracarboxylic dianhydride.


**Matrimid 5218**

Most preferably, the membranes of the invention are prepared from a polyimide polymer described in U.S. Patent No. 3,708,458, assigned to Upjohn. The polymer, available from HP Polymers, Inc., Lewisville, TX as Lenzing P84, is a copolymer derived from the co-condensation of benzophenone 3,3',4,4'-tetracarboxylic acid dianhydride (BTDA) and a mixture of di(4-aminophenyl) methane and toluene diamine or the corresponding diisocyanates, 4,4'-methylenebis(phenyl isocyanate) and toluene diisocyanate.

The obtained copolyimide has imide linkages which may be represented by the structural formulae:



AND


**Lenzing P84**

5

wherein the copolymer comprises from about 10 to 90% I and 90 to 10% II, preferably about 20% I and about 80% II.

10

Another polyimide useful to prepare a membrane in accordance with the invention is a polymer, available from HP Polymers, Inc., Lewisville, TX as Lenzing P84 HT. The polymer is the co-condensation of 1H,3H-Benzo[1,2-c:4,5-c']difuran-1,3,5,7-tetrone with 5,5'-carbonylbis[1,3-isobenzofurandione], 1,3-diisocyanato-2-methylbenzene and 2,4-diisocyanato-1-methylbenzene. The structure of the polyimide is shown below.



Lenzing P84 HT

Membranes in accordance with the invention can be made by dissolving the desired polyimide polymer in a solvent to give a viscous, polymer dope solution, spreading the solution upon a porous support to form a film, partially evaporating the solvent, and quenching the film in water. This precipitates the polymer and forms an asymmetric membrane by the phase inversion process.

The polyimide polymer dope solution is prepared by dissolving the polyimide polymer in one or a mixture of the following water-miscible solvents: N-methyl-2-pyrrolidone, hereinafter referred to as NMP, tetrahydrofuran, hereinafter referred to as THF, N,N-dimethylformamide, hereinafter referred to as DMF, dioxane, γ -butyrolactone, water, alcohols, ketones, and formamide.

The weight percent of the polyimide polymer in solution may range from 12% to 30% in the broadest sense, although a 18% to 28% range is preferable and a 20% to 26% range will produce the best results.

Additives such as viscosity enhancers may be present in amounts up to 10% by weight of the said polyimide polymer dope solution and these include

polyvinyl pyrrolidones, polyethylene glycols and urethanes. Additionally additives such as void suppressors may be used in amounts up to 5% of the weight of said polyimide polymer dope solution, and in this case maleic acid produces the desired results.

5 Once the polyimide polymer is dissolved in the solvent system described, it is cast onto a suitable porous support or substrate. The support can take the form of an inert porous material which does not hinder the passage of permeate through the membrane and does not react with the membrane material. the casting solution, the gelation bath solvent, or the
10 aromatic materials being separated. Typical of such inert supports are metal mesh, sintered metal, porous ceramic, sintered glass, paper, porous nondissolved plastic and woven or non-woven material. Preferably, the support material is a non-woven polyester, polyethylene, or polypropylene material.

15 Following the casting operation, a portion of the solvent may be evaporated under conditions sufficient to produce a dense, ultra-thin, top "skin" layer on the polyimide membrane. Typical evaporation conditions adequate for this purpose include air blown over the membrane surface at 15° to 25°C for a duration of less than 30 seconds.

20 The dense ultra-thin top "skin" layer of the asymmetric polyimide membranes of the invention is characterized by pore sizes below 50Å in diameter, is highly resistant to the greater than 500 psi operating pressures and has high operating efficiency and stability in the presence of solvent streams having a high aromatic content.

25 The coagulating or quenching medium may consist of water, alcohol, ketones or mixtures thereof, as well as additives such as surfactants, e.g., Triton X-100® available from Aldrich Chemical Company, Milwaukee, Wisconsin (octylphenoxy-polyethoxyethanol). The conditions for effecting coagulation are conventional.

The asymmetric polyimide membranes of the present invention can be washed and dried according to the following techniques. Typically a water-soluble organic compound such as low molecular weight alcohols and ketones including but not limited to methanol, ethanol, isopropanol, acetone, methylethyl ketone or mixtures thereof and blends with water can be used for removing the residual casting solvent (e.g., NMP) from the membrane. Alternatively the membrane may be washed with water. Removal of the residual casting solvent may require successive wash blends in a sequential solvent exchange process. Both membrane efficiency and flow rate can be enhanced by the proper solvent exchange process.

The membrane is then conditioned by contacting the membrane with a conditioning agent dissolved in a solvent to impregnate the membrane. The conditioning agent is a lubricating oil. Lubricating oils include, for example, synthetic oils (e.g., polyolefinic oils, silicone oils, polyalphaolefinic oils, polyisobutylene oils, synthetic wax isomerate oils, ester oils and alkyl aromatic oils) and mineral oils, including solvent refined oils and hydroprocessed mineral oils and petroleum wax isomerate oils. The lubricating oil may be a light neutral oil having a boiling temperature of 400-450°C to a heavy lubricating oil having a boiling temperature from 450-500°C. It is also within the scope of the invention to use other natural lubricating oils such as, for example, vegetable fats and oils, however, such fats and oils may be less desirable to avoid introducing unwanted contaminants into the process streams. Suitable solvents for dissolving the conditioning agent includes alcohols, ketones, aromatics, or hydrocarbons, or mixtures thereof.

The use of a conditioning agent in accordance with the invention allows the membrane to maintain a high flux while exhibiting a high selectivity to permeate aromatics in the presence of non-aromatics. The conditioning agent also allows the membrane to be wetted with hydrocarbon

solvents, to maintain a suitable pore structure in a dry state for permeation of aromatics, and to produce a flat sheet membrane with improved flexibility and handling characteristics.

Following treatment with the conditioning agent, the membrane is typically dried in air at ambient conditions to remove residual solvent. Preferably the membrane is dried in a forced air drying oven designed to capture solvent emissions.

Heat treatment can also be used to increase membrane rejection of non-aromatic hydrocarbons. After the conditioning step, the membrane may be heated to about 150°C to about 320°C, preferably about 200°C for about 1 minute to 2 hours. At about 200°C, the heating time is typically about 5 minutes. It is preferred that the membrane be air dried before heating.

Once the membranes are formed they may be processed into spiral wound modules, into hollow fiber configurations, into flat sheet or into plate and frame configurations.

In the practice of a preferred embodiment of the present invention, a feed stream containing the aromatic hydrocarbons and non-aromatic hydrocarbons to be separated will be contacted with the dense active layer side of the polyimide membrane under pressure and at a temperature sufficient to effect the desired separation. Such contacting will typically be at about -20°C to about 150°C, preferably about 20°C to about 80°C. The pressure employed will be at least greater than that sufficient to overcome the osmotic pressure difference between the feed stream and the permeate stream. Preferably there will be at least a net driving force of about 100 to 1000 psi across the membrane, more preferably a net driving force of about 400 to 1000 psi, most preferably about 600 to 800 psi. Preferably, no additional heating or cooling of the stream is made to minimize energy requirements.

The membranes of the invention are preferably used in accordance with the invention as described in co-pending Application Serial No. 126,256,

filed July 30, 1998, entitled "Recovery of Aromatic Hydrocarbons Using Lubricating Oil Conditioned Membranes", Mobil Attorney Docket No. 10043-1, filed on even date herewith. In accordance with the co-pending application, the invention membranes are contacted with a feed stream having at least 10 wt% of aromatic hydrocarbons. In a preferred embodiment, the membranes are contacted with a feed stream containing an aromatic hydrocarbon content of above 50 wt %, most preferably 70 wt % or higher. In one embodiment the feed stream contains an aromatic hydrocarbon content of 80 wt % or higher, preferably 90 wt % or higher.

The membranes of the invention can be used to upgrade aromatics containing streams in petroleum refineries, such streams including, naphtha streams, heavy catalytic naphtha streams, intermediate catalytic naphtha streams, light aromatic streams and reformat streams. The membranes are also useful in commercial chemical operations for the recovery of aromatics such as, for example, benzene, toluene, xylene, and alkyl naphthalene. Of particular interest, the membranes of invention can have application at various points in a commercial aromatics, i.e. toluene, production unit to upgrade the aromatics content of process streams. It is within the scope of the invention to use the invention membranes alone or in combination with other adsorption, distillation, extraction or reforming processes. When used in a hybrid process with other separation technologies, the invention membrane is not required to make 100 % separation of aromatics from non-aromatics, but can instead be used to perform partial separation of aromatics to complement overall separation processes. The membrane of the invention thus offers excellent efficiencies in bulk separation processes which when coupled with other more selective unit operations can offer enhanced performance.

The Examples below are for illustrative purposes only, and do not limit the invention, or the claims which follow them.

EXAMPLES

In the cases shown here, the asymmetric polyimide membranes preferentially permeate aromatic over non-aromatic hydrocarbons. The membranes were tested on a small bench unit with four (4) test cells in series under reverse osmosis conditions. The feed solution was continuously flushed over the membrane surfaces, and the permeate and retentate streams were combined and recycled. A typical feed solution consists of a high toluene concentration (80-100%), along with lesser amounts of other aromatic compounds such as benzene and p-xylene and non-aromatic hydrocarbons including branched and unbranched C6 to C9 isomers. The feed was pressurized, heated to operating temperatures, and pumped over the surface of the membrane. If desired, permeate lines could also be pressurized. Permeate samples were generally collected after overnight operation (18+ hours).

Membrane coupons were small disks with 14.2 cm² surface area. Flows were determined in ml/min and then converted to gallons per square foot per day (GFD). Sample sizes were kept at less than 1% by weight of material, so that retentate and feed compositions were essentially equal. GC analysis was used to identify concentrations of aromatic and non-aromatic compounds. All concentrations were expressed as weight percent. Rejection was calculated from the sum of non-aromatic compounds in both the permeate and retentate streams with the formula $\text{Rejection (\%)} = (1 - \% \text{ per} / \% \text{ ret}) \times 100\%$. In some cases, specific rejections for a given hydrocarbon were calculated.

Example 1

A viscous solution containing 22% Lenzing P84 polyimide (HP Polymers, Inc., Lewisville, TX), 67% dioxane, and 11% dimethylformamide (DMF) was prepared and filtered through a 10 micron filter. This solution was cast at 10 ft/min onto a moving web of nonwoven polyester fabric (Hollytex

3329 from Ahlstrom Filtration, Mt. Holly Springs, PA) using a knife blade set at a gap of 7 mil above the fabric. After about 15 seconds with an air flow of 1 SCFM the coated fabric was quenched in water at 22°C to form the membrane structure. The membrane was washed with water to remove residual solvents, then solvent exchanged by immersion into methyl ethyl ketone (MEK) for 3 hours, followed by immersion in a solution of 20% light neutral lube oil/40% MEK/40% toluene for 3 hours. The membrane was then air dried.

The membranes were tested as flat sheet coupons at 50°C and 800 psi with various circulating solutions consisting of a high toluene concentration and additional aromatic and non-aromatic C6 to C9 hydrocarbons typically found in a toluene process stream in refinery operations. Total aromatic content in one of the feeds was 99.37 wt%.

The membrane exhibited good rejection (54%) of non-aromatics and a flux of 22.9 GFD. The aromatic content in the permeate was 99.71 wt%.

Example 2

A viscous solution containing 24% Lenzing P84 polyimide (HP Polymers, Inc., Lewisville, TX), 56% dioxane, and 20% dimethylformamide (DMF) was prepared. This solution was cast at 4 ft/min onto a moving web of nonwoven polyester fabric (Hollytex 3329 from Ahlstrom Filtration, Mt. Holly Springs, PA) using a knife blade set at a gap of 7 mil above the fabric. After about 3 seconds with an air flow of 20 SCFH the coated fabric was quenched in water at 20°C to form the membrane structure. The membrane was washed with water to remove residual solvents, then solvent exchanged by immersion into methyl ethyl ketone (MEK) for 1 hour, followed by immersion in a second solvent exchange bath of light neutral lube oil in 50/50 MEK/toluene for 1 hour. The membrane was then air dried.

A series of Lenzing P84 membranes with differing oil content were prepared by changing levels of oil in the 2nd exchange bath from 0 to 60% oil, while maintaining a 50/50 ratio of MEK/toluene.

5 A feed solution consisting of 88 wt% toluene with six compounds (n-decane (C10), 1-methylnaphthalene (C11), n-hexadecane (C16), 1-phenylundecane (C17), pristane (C19), and n-docosane (C22) each at 2% levels was prepared. Coupons of each membrane were tested at 600 psi and 50°C. Results are recorded in Table 1 below.

10

Table 1

Oil Content in 2nd Solvent Exchange Bath (%)	Flux (GFD)	C10 Rejection (%)
0	2.4	65
20	25.3	45
33	26.3	43
50	27.7	42
60	27.4	42

15 The membrane having no lube oil present as a conditioning agent had an unacceptably low flux. The membranes conditioned with lube oil exhibited over 40% rejection of non-aromatic with a significant increase in flux (GFD) over the unconditioned membrane.

Example 3

20 A viscous solution containing 26% Matrimid 5218 polyimide (Ciba Geigy, Hawthorne, NY), 15% acetone, and 59% dimethylformamide (DMF) was prepared and filtered through a 10 micron filter. This solution was cast at 10 ft/min onto a moving web of nonwoven polyester fabric (Hollytex 3329 from Ahlstrom Filtration, Mt. Holly Springs, PA) using a knife blade set at a

gap of 8 mil above the fabric. After about 15 seconds with an air flow of 1 SCFM the coated fabric was quenched in water at 22°C to form the membrane structure. The membrane was washed with water to remove residual solvents, then solvent exchanged by immersion into methyl ethyl ketone (MEK) for 3 hours, followed by immersion in a solution of 20% light neutral lube oil/40% MEK/40% toluene for 3 hours. The membrane was then air dried.

A feed solution consisting of 94 wt% toluene with three non-aromatic compounds (n-decane, n-hexadecane, and n-docosane) each at 2% levels was prepared. Coupons of each membrane were tested at 600 psi and 50°C.

The membrane demonstrated 25% rejection of n-decane, 51% rejection of n-hexadecane and 68% rejection of n-docosane with a flux of 18.0 GFD.

Example 4

A Lenzing P84 membrane was prepared as in Example 2 and with the second solvent exchange bath containing 33% oil. An annealed membrane was prepared by clipping a sample to a glass plate, and heating in an oven at 220°C for set times. The samples were tested with a toluene solution under pressure as in Example 2. Results are recorded in Table 2 below.

Table 2

Flux and Rejection for Lenzing P84 Membrane at 600 psi and 50°C

Anneal Time (minutes)	Flux (GFD)	Rejection (%)					
		C10	C11	C16	C17	C19	C22
0	29.7	45	0	75	70	83	95
2	19.3	54	0	74	63	81	95
4	17.4	59	16	88	84	97	100
6	9.4	66	27	83	75	88	100
8	3.9	75	34	91	100	100	100

Rejection of the non-aromatic components by the membrane increased with heat treatment of the membrane.

Example 5

5 An annealed Lenzing P84 membrane was prepared as in Example 4 by clipping a sample to a glass plate, and heating in an oven at 180°C for 5 minutes. Coupons of this membrane were tested with a toluene stream obtained from a refinery. The non-aromatics in this sample were isomers of C7 and C8 including methyl heptanes, ethyl hexanes, dimethyl hexanes, 10 methyl ethyl pentanes, trimethyl pentanes, methyl ethyl cyclopentanes, trimethyl cyclopentanes, and dimethyl cyclohexanes. Results are recorded in Table 3 below.

Table 3

15 Rejection and Flux for Lenzing P84 Membrane at 800 psi and 58°C

	Benzene (%)	Toluene (%)	p-Xylene (%)	% Non- Aromatics	Flux (GFD)	Non- Aromatics Rejection (%)
Feed	0.10	94.89	0.28	4.73		
Permeate	0.10	97.58	0.28	2.04	34.7	57

As shown in Table 3, the membrane exhibited favorable rejection of non-aromatics at favorable process conditions and permeate flow rates.

20

Example 6

A viscous solution containing 24% Lenzing P84 HT polyimide (HP Polymers, Inc., Lewisville, TX), 38% dioxane, and 38% dimethylformamide (DMF) was prepared. This solution was cast at 4 ft/min onto a moving web of

nonwoven polyester fabric (Hollytex 3329) using a knife blade set at a gap of 7 mil above the fabric. After about 3 seconds with an air flow of 10 SCFH the coated fabric was quenched in water at 21 °C to form the membrane structure. The membrane was washed with water to remove residual solvents, then solvent
 5 exchanged by immersion into MEK for 1 hour, followed by immersion in a solution of 33% light neutral lube oil/33% MEK/33% toluene for 1 hour. The membrane was then air dried.

Coupons were tested with a 230-270°C distillation cut of light cycle oil containing a high percentage of aromatic compounds. The percentage of 1-ring,
 10 2-ring, and 3-ring aromatics and non-aromatic compounds were determined with supercritical fluid chromatography methods. Results from coupon tests at 1000 psi and 57°C are reported in Table 4.

Table 4

Rejection and Flux for Lenzing P84 HT Membrane

	Flux (GFD)	Non- aromatics (%)	1-ring aromatics (%)	2-ring aromatics (%)	3-ring aromatics (%)	Non-aromatics rejection (%)
Feed		16.2	10.3	73.5	0.0	
Permeate	1.1	8.5	8.1	83.4	0.0	47

Example 7

A viscous solution containing 22% Lenzing P84 polyimide, 11%
 20 acetone, and 67% N-methyl-2-pyrrolidone (NMP) was prepared. This solution was cast at 4 ft/min onto a moving web of non-woven polyester fabric (Hollytex 3329) using a knife blade set at a gap of 7 mil above the fabric. After about 3 seconds the coated fabric was quenched in water at 22 °C to form the membrane structure. The membrane was washed with water to remove residual solvents,

then solvent exchanged by immersion into MEK for 1 hour, followed by immersion in a solution of 40% light neutral lube oil/30% MEK/30% toluene for 1 hour. The membrane was then air dried.

A feed solution was obtained from a refinery and consisted of three components, 11% p-xylene, 15% 1-methylnaphthalene, and 74% of a light neutral lube distillate. Coupons were tested at 600 psi and 107 °C. The lube distillate component of the feed was fractionated by refining processes into an aromatic-rich extract oil fraction and a non-aromatic-rich raffinate oil fraction. Analysis of the feed and permeate solutions and the refinery extract and raffinate fractions were performed with GC and UV/visible spectrometry. By monitoring the absorption at 350 nm in methylene chloride, an estimate of the percentage of aromatic-rich extract oil was determined. Results are recorded in Table 5 below.

Table 5


Fractionation of Lube Distillate Oil with Lenzing P84 Membrane

	Flux (GFD)	p-xylene (%)	1-methyl- naphthalene (%)	lube distillate (%)	est. % extract oil in lube distillate	est. % raffinate oil in lube distillate
Feed		11.0	14.8	74.2	43.7	56.3
Permeate	4.1	12.9	17.4	69.7	49.8	50.2


As shown in Table 5, the membrane showed good rejection of non-aromatics as indicated by the increased aromatic content in the permeate.

IN THE CLAIMS:


1. An asymmetric polyimide membrane treated with a conditioning agent comprising a lubricating oil, the membrane having a sufficient flux and selectivity to separate aromatic hydrocarbons from non-aromatic hydrocarbons in a feed stream under hyperfiltration conditions.
2. A membrane for recovery of aromatic hydrocarbons comprising an asymmetric polyimide membrane impregnated with a lubricating oil, wherein the polyimide is a copolymer derived from the co-condensation of benzophenone 3,3', 4,4'-tetracarboxylic acid dianhydride and a mixture of di(4-aminophenyl) methane and toluene diamine, or a mixture of 4,4'-methylenebis (phenyl isocyanate) and toluene diisocyanate.
3. The asymmetric membrane of Claim 2 wherein the polyimide is a polyimide copolymer comprising from 10 to 90% of




and from 90 to 10% of



4. The asymmetric polyimide membrane of Claim 3 wherein the polyimide copolymer employed comprises about 20% of



and about 80% of



5. The asymmetric membrane of Claim 1 wherein the lubricating oil is a synthetic oil.

6. The asymmetric membrane of Claim 5 wherein the synthetic oil is a silicone oil, a polyolefinic oil, a polyalphaolefinic oil, a polyisobutylene oil, a synthetic wax isomerate oil, an ester oil or an alkyl aromatic oil.

7. The asymmetric membrane of Claim 1 wherein the lubricating oil is a mineral oil.

8. The asymmetric membrane of Claim 7 wherein the mineral oil is a solvent refined mineral oil, a petroleum wax isomerate oil or a hydroprocessed mineral oil.

9. The asymmetric membrane of Claim 2 wherein the lubricating oil is a synthetic oil.

10. The asymmetric membrane of Claim 9 wherein the synthetic oil is a silicone oil, a polyolefinic oil, a polyalphaolefinic oil, a polyisobutylene oil, a synthetic wax isomerate oil, an ester oil or an alkyl aromatic oil.

11. The asymmetric membrane of Claim 2 wherein the lubricating oil is a mineral oil.

12. The asymmetric membrane of Claim 11 wherein the mineral oil is a solvent refined mineral oil, a petroleum wax isomerate oil or a hydroprocessed mineral oil.

13. The asymmetric membrane of Claim 3 wherein the lubricating oil is a synthetic oil.

14. The asymmetric membrane of Claim 13 wherein the synthetic oil is a silicone oil, a polyolefinic oil, a polyalphaolefinic oil, a polyisobutylene oil, a synthetic wax isomerate oil, an ester oil or an alkyl aromatic oil.

15. The asymmetric membrane of Claim 3 wherein the lubricating oil is a mineral oil.

16. The asymmetric membrane of Claim 15 wherein the mineral oil is a solvent refined mineral oil, a petroleum wax isomerate oil or a hydroprocessed mineral oil.

17. The asymmetric membrane of Claim 1 wherein the membrane is supported on a porous support material.

18. The asymmetric membrane of Claim 17 wherein the support material is a non-woven material.

19. The asymmetric membrane of Claim 18 wherein the non-woven material is a polyester, polyethylene or polypropylene material.

20. A process for preparing a polyimide asymmetric membrane for the permselective separation of aromatic hydrocarbons from non-aromatic hydrocarbons under hyperfiltration conditions comprising

(a) preparing a polyimide dope solution comprising a polyimide co-polymer derived from (1) the co-condensation of benzophenone 3,3',4,4'-tetracarboxylic acid dianhydride (BTDA) and a mixture of di(4 aminophenyl) methane and toluene diamine or a mixture of 4,4'-methylenebis(phenyl isocyanate) and toluene diisocyanate; or (2) the co-condensation of 1H,3H-Benzo[1,2-c:4,5-c']difuran-1,3,5,7-tetrone with 5,5'-carbonylbis[1,3-isobenzofurandione], 1,3-diisocyanato-2-methylbenzene and 2,4-diisocyanato-1-methylbenzene, dissolved in a water miscible solvent in amounts of 20 to 28 by weight of said dope solution;

(b) casting said polyimide dope solution onto a porous support substrate to form a film;

(c) partially evaporating the solvent from the film;

(d) immersing the film obtained from step (c) into a coagulating medium to form an asymmetric membrane; and

(e) contacting the asymmetric membrane with at least one wash bath containing a conditioning agent comprising a lubricating oil.

21. The process of Claim 20 further comprising as step (f) drying the conditioned membrane of step (e).

22. The process of Claim 20 wherein the water-miscible solvent used to prepare the polyimide dope solution is selected from the group consisting of N-methyl-2-pyrrolidone, tetrahydrofuran, N,N-dimethylformamide, dioxane, γ -butyrolactone, water, alcohols, ketones, formamide, and mixtures thereof.

23. The process of Claim 20 wherein the polymer dope solution further comprises a viscosity enhancer in amounts of less than 10% by weight of said dope solution, said viscosity enhancer consisting essentially of polyvinyl pyrrolidones, polyethylene glycols or urethanes.

24. The process of Claim 20 wherein the polymer dope solution further comprises a void suppresser in amounts of less than 5% by weight of said dope solution.

25. The process of Claim 24 wherein the void suppresser consist essentially of maleic acid.

26. The process of Claim 20 wherein the coagulating medium consist essentially of water, alcohol, ketones or mixtures thereof.

27. The process of Claim 21, wherein after step (f), optionally heating the membrane at 150°C or higher for up to 2 hours.

28. The process of Claim 20 wherein the porous support substrate in step (b) is non-woven polyester, polypropylene or polyethylene.

29. The process of Claim 20 wherein the conditioning agent in step (e) is a synthetic oil.

30. The process of Claim 20 wherein the conditioning agent is a mineral oil.

31. The process of Claim 30 wherein the mineral oil is a solvent refined mineral oil, a petroleum wax isomerate oil or a hydroprocessed mineral oil.

32. The process of Claim 29 wherein the synthetic oil is silicone oil, a polyolefinic oil, a polyalphaolefinic oil, polyisobutylene oil, a synthetic wax isomerate oil, an ester oil or an alkyl aromatic oil.

33. A membrane for recovery of aromatic hydrocarbons comprising an asymmetric polyimide membrane impregnated with a lubricating oil, wherein the polyimide is a copolymer derived from the condensation of 1H,3H-Benzo[1,2-c:4,5-c']difuran-1,3,5,7-tetrone with 5,5'-carbonylbis[1,3-isobenzofurandione], 1,3-diisocyanato-2-methylbenzene and 2,4-diisocyanato-1-methylbenzene.

34. The asymmetric membrane of Claim 33 wherein the lubricating oil is a synthetic oil.

35. The asymmetric membrane of Claim 34 wherein the synthetic oil is a silicone oil, a polyolefinic oil, a polyalphaolefinic oil, a polyisobutylene oil, a synthetic wax isomerate oil, an ester oil or an alkyl aromatic oil.

36. The asymmetric membrane of Claim 33 wherein the lubricating oil is a mineral oil.

37. The asymmetric membrane of Claim 36 wherein the mineral oil is a solvent refined mineral oil, a petroleum wax isomerate oil or a hydroprocessed mineral oil.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 99/15603

A. CLASSIFICATION F SUBJECT MATTER IPC 7 B01D71/64 B01D61/02 B01D69/12 C10G31/11		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 7 B01D C10G		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 94 25146 A (GRACE W R & CO) 10 November 1994 (1994-11-10)	1,5-8, 17-19, 33-37
Y	page 7, line 4 -page 11, line 13; claims 1-3,5,6,9-12; examples 1-6	2-4, 9-16, 20-32
Y	EP 0 483 999 A (EXXON RESEARCH ENGINEERING CO) 6 May 1992 (1992-05-06) page 3, line 30 - line 36 page 4, line 24 - line 29 <div style="text-align: center;">-/-</div>	2-4, 9-16, 20-32
<div style="display: flex; justify-content: space-between;"> <input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex. </div>		
* Special categories of cited documents :		
<div style="display: flex; justify-content: space-between;"> <div style="width: 45%;"> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> </div> <div style="width: 45%;"> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"&" document member of the same patent family</p> </div> </div>		
Date of the actual completion of the international search <div style="text-align: center;">26 October 1999</div>		Date of mailing of the international search report <div style="text-align: center;">08/11/1999</div>
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040. Tx. 31 651 epo nl, Fax: (+31-70) 340-3016		Authorized officer <div style="text-align: center;">Edmüller, P</div>

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 99/15603

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>EP 0 125 907 A (EXXON RESEARCH ENGINEERING CO) 21 November 1984 (1984-11-21)</p> <p>page 2, line 27 -page 3, line 27 page 4, line 1 -page 5, line 19 page 11, line 4 - line 9; figure 2; examples 1-3</p>	<p>1-4,7,8, 11,12, 15-20, 22,26, 28,30, 31,33, 36,37</p>
X	<p>US 4 532 041 A (EXXON RESEARCH ENGINEERING) 30 July 1985 (1985-07-30)</p> <p>column 3, line 6 -column 6, line 39 claims 1,8-12; figure 1; examples 1-22</p>	<p>1-4,7,8, 11,12, 15-20, 22,26, 28,30, 31,33, 36,37</p>

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/15603

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9425146 A	10-11-1994	US 5264166 A AT 170097 T AU 6410194 A DE 69412811 D DE 69412811 T EP 0695213 A ES 2122259 T US 5429748 A	23-11-1993 15-09-1998 21-11-1994 01-10-1998 29-04-1999 07-02-1996 16-12-1998 04-07-1995
EP 0483999 A	06-05-1992	CA 2052982 A JP 4282325 A US 5133867 A	28-12-1991 07-10-1992 28-07-1992
EP 0125907 A	21-11-1984	CA 1262880 A DE 3468432 A JP 60035091 A SG 74189 G	14-11-1989 11-02-1988 22-02-1985 20-04-1990
US 4532041 A	30-07-1985	CA 1262807 A EP 0125908 A JP 59230604 A	14-11-1989 21-11-1984 25-12-1984